



TESTING SERVICES, INC.
 817 SHOWALTER AVE. • P.O. BOX 2041
 DALTON, GEORGIA 30722-2041
 PHONE: (706) 226-1400 • FAX: (706) 226-6118



TEST REPORT

CLIENT:	West Coast Rubber, LLC	REPORT NUMBER:	48748B
	1501 Lana Way	LAB TEST NUMBER:	2176-3134
	Hollister, CA 95023	DATE:	July 15, 2010

TEST MATERIAL:

Identification
GroundRubber Play (loose fill recycled rubber mulch) Compacted to 9" depth

INTRODUCTION:

Testing Services Inc was instructed by the client, to perform ADA wheelchair accessibility for the above test material being used under and around playground equipment.

TEST METHOD:

ASTM F1951-09b: *Standard Specification for Determination of Accessibility of Surface Systems Under and Around Playground Equipment*

REQUIREMENT:

A surface in place shall have average work per foot (work per meter) values for straight propulsion and for turning, **less** than the average work per foot (work per meter) values for straight propulsion and for turning, respectively, on a hard, smooth, surface with a grade of 1:14 (7.1 %).

PROCEDURE:

Test Surface Preparation: Tests were conducted on July 7, 2010 indoors at TSi Laboratories in an environment of 89°F and 46% R.H. The rubber mulch was installed in a wooden box (44"W x 117"L x 9" Thick). The system, prior to testing, was slightly compacted using a water-filled lawn roller to simulate foot traffic.

Wheelchair/Operator: The wheelchair used in these tests was manufactured by *Invcare*, Model Action Xtra, serial Number 98J84142. This wheelchair is totally adjustable, a necessity for these tests. The pneumatic tires were inflated to 60 psi on the rear and 32 psi on the front. The weight of the wheelchair was 24.25 pounds and the operator's weight was 165 pounds for a total of 189 pounds. The operator's distribution was adjusted to 60% on the rear wheels and 40 % on the front.

Torque Measuring System: A certified *Dillion Electronic Force Gauge*, Model BFG 500N, S/N 98-2277-07 was used as an interface between a *Dell Laptop* and a certified *Dillion Smart Torque Wrench*, S/N 97-0085-01. Software, also from Dillon, logged the load vs. time and integrated the area under the resulting curves. The adapters and accessories needed to attach the instrumentation were fabricated locally. This total package added 10 pounds to the total weight bringing the total to 199 pounds.



TESTING SERVICES, INC.
 817 SHOWALTER AVE. • P.O. BOX 2041
 DALTON, GEORGIA 30722-2041
 PHONE: (706) 226-1400 • FAX: (706) 226-6118



Attachment to Report # 48748B

West Coast Rubber, LLC
 1501 Lana Way
 Hollister, CA 95023
 Page 2 of 2

TEST RESULTS:

Straight Line Propulsion

Baseline Straight (Average Work/ft-Force)	GroundRubber Play Straight (Average Work/ft-Force)
14.86 lbs	13.44 lbs

Turning Propulsion

Baseline Turning (Average Work/ft-Force)	GroundRubber Play Turning (Average Work/ft-Force)
10.36 lbs	9.33 lbs

CONCLUSION:

The above test material **meets/exceeds** both the straight line and turning propulsion requirements set forth in this test method and therefore, passes the standard.

Approved By:

 Erle Miles, Jr. VP
 Testing Services Inc